

Highway Safety Corporation

Glastonbury, CT

Welding Procedure Specification

Material specification ASTM A36, A572 gr 50, A709 Gr 36, ASTM A709 Gr 50, A500 gr B
 Welding process Gas Metal Arc Welding (GMAW)
 Manual, semi-automatic, or automatic Semi-Automatic
 Position of welding Horizontal (2F)
 Filler metal specification AWS A5.18
 Filler metal classification ER70S-3
 Electrode and manufacturer Lincoln Electric Lincoln Weld L-50
 Flux and manufacturer NA
 Shielding gas 85% Argon / 15% CO2 Flow rate 19-27 L / min
 Single or multiple pass Single & Multiple
 Single or multiple arc Single
 Welding current DC
 Polarity Reverse
 Welding progression Stringers
 Root treatment None
 Preheat and interpass temperature Base Metal up to 3/4" (50°F) ; over 3/4-1 1/2" (70°F)
 Postheat treatment None
 Electrode extension 3/4" ± 1/4"

WELDING PROCEDURE

| Weld size | Pass no. | Electrode size | Welding parameters | | Travel speed | Joint detail |
|--------------------|----------|----------------|--------------------|-------------|---------------|---|
| | | | Amperes | Volts | | |
| 7/16" x 1/4" | 1 & 2 | 0.045" | 300 A ± 30 | 29 V ± 2 | 14 ipm ± 2 | <p>UN-EQUAL LEG FILLET WELD @ BASE PLATE CONNECTION</p> |

Handwritten notes: VTRAWS RECEIVED JUN 9 2007 6/19/07

This procedure may vary due to fabrication sequence, fit-up, pass size, etc. within the limitation of variables given in section 5 of latest edition AWS D1.1

WPS no. W-1587-2
 Revision no. 1 6/19/2007
 Supporting PQR no. Pre-qualified
 Project Name Ryegate, Vermont

Fabricator Highway Safety Corporation
 Authorized by Paul Radice
 Date 5/15/07
 Project Number ACIM 091-2(73)

