

WELDING PROCEDURE SPECIFICATION
PQR ELDERLEE #3

Material Specification	A500 TO A36	
Welding Process	FCAW-G	
Manual or Machine	SEMAUTOMATIC	
Position of Welding	FLAT/HORIZONTAL	
Filler Metal Specification	A5.29	
Filler Metal Classification	E81T1-Ni1C-JH4	
Flux	N/A	
Shielding Gas	CO 2	Dew Point -40DEG F Flow Rate 50CFH
Single or Multiple Pass	SINGLE	
Single or Multiple Arc	SINGLE	
Welding Current	DC	
Polarity	REVERSE	
Welding Progression	STRINGER	
Root Treatment	CLEAN PER D1.5	
Preheat and Interpass Temperature	PER D1.5	
Postheat Temperature	NONE	
Heat Input	Min _____	Max _____

WELDING PROCEDURE

Pass no.	Electrode size	Welding Current		Travel speed	Joint detail
		Amperes	Volts		
	1/16	310	25	11	
Variable	LIMITS	341 TO 269	27 TO 23	12 TO 10	
<p>Trans Received OK'd BY <i>Jax</i></p> <p>AUG 06 2014</p> <p>Resubmit BY _____ APPROVED DATE <i>8/12/14</i></p>					

This procedure may vary due to fabrication sequence, fit-up, pass size, etc., within the limitation of variables given in Section 5.

Procedure No. 3026
Revision No. _____

Contractor Elderlee, Inc.
Authorized By RANDY SCOTT
Date 3/24/2014