

# Highway Safety Corporation

Glastonbury, CT

## Welding Procedure Specification

Material specification A572 gr 50, A709 Gr 50  
 Welding process Gas Metal Arc Welding (GMAW) Spray Transfer  
 Manual, semi-automatic, or automatic Semi-Automatic  
 Position of welding Flat (1F) or Horizontal (2F)  
 Filler metal specification AWS A5.18  
 Filler metal classification ER70S-6  
 Electrode and manufacturer Lincoln Electric Lincoln Weld L-56  
 Flux and manufacturer N/A  
 Shielding gas 86% Argon / 14% CO2 Flow rate 35-45 CFM  
 Single or multiple pass Single or Multiple  
 Single or multiple arc Single  
 Welding current DCEP  
 Polarity Reverse - electrode positive  
 Welding progression Stringers  
 Root treatment clean base metal  
 Preheat and interpass temperature base metal up to 3/4" (50°F) ; over 3/4 thru 1-1/2" ( 150°F ) ; over 1-1/2" thru 2-1/2" (225°F)  
 Postheat treatment None  
 Electrode extension 3/4" ± 1/4"

**APPROVED**  
 By Ryan Foster at 9:42 am, May 12, 2015

### WELDING PROCEDURE

Weld size	Pass no.	Electrode size	Welding parameters		Travel speed	Joint detail
			Amperes	Volts		
5/16"	1	0.062"	300 A ± 30	29 V ± 2	15 ipm ± 2	
7/16"	1 & 2	0.062"	↓	↓	15 ipm ± 2	

This procedure may vary due to fabrication sequence, fit-up, pass size, etc. within the limitation of variables given in section 5 of latest edition AWS D1.5

WPS no. <u>W-VTPEDPOST1</u>	Fabricator <u>Highway Safety Corporation</u>
Revision no. <u>0</u>	Prepared By: <u>Paul Radice</u>
Supporting PQR no. <u>Pre-Qualified</u>	Date <u>4/8/15</u>
Project Name <u>Castleton, VT</u>	Project Number <u>BRF 015-2(10)</u>