

# Highway Safety Corporation

Glastonbury, CT

## Welding Procedure Specification

Material specification A572 gr 50, A709 Gr 50  
 Welding process Gas Metal Arc Welding (GMAW)  
 Manual, semi-automatic, or automatic Semi-Automatic  
 Position of welding Flat (1F) or Horizontal (2F)  
 Filler metal specification AWS A5.18  
 Filler metal classification ER70S-3  
 Electrode and manufacturer Lincoln Electric Lincoln Weld L-50  
 Flux and manufacturer N/A  
 Shielding gas 85% Argon / 15% CO2 Flow rate 19-27 L / min  
 Single or multiple pass Single or Multiple  
 Single or multiple arc Single  
 Welding current DCEP  
 Polarity Reverse - electrode positive  
 Welding progression Stringers  
 Root treatment clean base metal  
 Preheat and interpass temperature base metal up to 3/4" (50°F) ; over 3/4 thru 1-1/2" ( 150°F ) ; over 1-1/2" thru 2-1/2" (225°F)  
 Postheat treatment None  
 Electrode extension 3/4" ± 1/4"

### WELDING PROCEDURE

Weld size	Pass no.	Electrode size	Welding parameters		Travel speed	Joint detail
			Amperes	Volts		
5/16"	1	0.062"	275 A ± 25	25 V ± 2	8-10 ipm	
7/16"	1 & 2	0.062"	↓	↓	8-10 ipm	

VT RAILS RECEIVED

CK'D BY \_\_\_\_\_ OK'D BY JWC

NOV 04 2010

RESUBMIT \_\_\_\_\_ APPROVED ✓

BY \_\_\_\_\_ DATE 11/16/10

This procedure may vary due to fabrication sequence, fit-up, pass size, etc. within the limitation of variables given in section 5 of latest edition AWS D1.5

WPS no. W-1785A  
 Revision no. 0  
 Supporting PQR no. Pre-Qualified  
 Project Name Cornwall, VT  
 Fabricator Highway Safety Corporation  
 Prepared By: Paul Radice  
 Date 11/4/10  
 Project Number BRS 0172 (6)

Paul A Radice  
 CWI 98070221  
 QC1 EXP. 7/1/2013