

Highway Safety Corporation

Glastonbury, CT

Welding Procedure Specification

Material specification ASTM A36, A572 gr 50, A709 Gr 36, ASTM A709 Gr 50, A500 gr B, A53 gr B
 Welding process Gas Metal Arc Welding (GMAW) Spray Transfer
 Manual, semi-automatic, or automatic Semi-Automatic
 Position of welding Flat (1F) or Horizontal (2F)
 Filler metal specification AWS A5.18
 Filler metal classification ER70S-6
 Electrode and manufacturer Lincoln Electric Lincoln Weld L-56
 Flux and manufacturer N/A
 Shielding gas 86% Argon / 14% CO2 Flow rate 35-45 CFM
 Single or multiple pass Single
 Single or multiple arc Single
 Welding current DCEP
 Polarity Reverse - electrode positive
 Welding progression Stringers
 Root treatment clean base metal
 Preheat and interpass temperature base metal up to 3/4" (50°F)
 Postheat treatment None
 Electrode extension 3/4" ± 1/4"

Vermont Agency of Transportation

RECEIVED

CK'D BY RK/JC

OK'D BY RY

February 20, 2015


RESUBMIT No

Approved

BY RY

DATE 03/09/2015

WELDING PROCEDURE

Weld size	Pass no.	Electrode size	Welding parameters		Travel speed	Joint detail
			Amperes	Volts		
n/a	1	0.063	300 A	29	15 ipm	<p><u>TC-U4b-GF</u></p>  <p>X = 45 As Fitup: X=+10, -5 All Thicknesses</p>
			+/- 30	+/- 3	+/- 2	

This procedure may vary due to fabrication sequence, fit-up, pass size, etc. within the limitation of variables given section 5 of latest edition AWS D1.1 / D1.5

AWS
 Paul A Radice
 CWI 98070221
 QC1 EXP. 7/1/2016

WPS no. W-2030-B Fabricator Highway Safety Corporation
 Revision no. 0 Prepared By: Paul Radice
 Supporting PQR no. Pre-Qualified Date 02-18-15
 Project Name Fairfield, Vermont Project Number BRF0281 (25) / BRO 1448(41)