



Production Joint Welding Procedure Specification (D1.5-02)

Procedure No: A-(MC)GF-01 Date Issued: 9-28-04 Revision No: 0 Rev. Date: _____

Contractor (Fabricator) D. S. Brown Company Prepared by: James R. Connor, Quality Assurance Manager

1. Non-Fracture Critical Fracture Critical WPS Expiration Date: _____

2. Qualified in accordance with: AWS D1.5-2002 (5.12.1)

Referenced PQR No(s) PQR-(MC)GMAW-01(04)

Referenced FWST No(s) PQR-(MC)GMAW-FWST-01A(04), PQR-(MC)GMAW-FWST-01B(04)

3. Material specification(s) ASTM A709 Gr. 36, 50, 50W

For DOT Approval

4. Material Thickness (es) Unlimited

5. Welding process GMAW

6. Manual , machine , or semiautomatic

7. Position(s) of welding 1F, 2F

8. Filler metal specification AWS A5.18

9. Filler metal class and brand name E70C-6M Corex Metal-Core Maxim

10. Flux class & brand N/A, Type N/A

11. Shielding gas 75% Ar / 25% CO2 Flow rate 45 CFH

12. Single pass Or multiple pass

13. Single arc Or multiple arc

14. Welding Current DCEP

15. Polarity Reverse

16. Welding progression stringers

17. Root treatment Clean to bright sound metal or per AWS D1.5 (3.2.1 & 3.11)

18. Postheat treatment N/A

19. Calculated Heat Input (KJ/in) Min 30.6 KJ/in Max 51.1 KJ/in

20. Electrode extension (electrical stickout) 3/4"

V.A.O.T.
RECEIVED
ORDER BY JJC
NOV 16 2004
REVISIONS APPROVED
BY DATE 11-30-04

Weld Size (in)	Passes	Electrode Size (in)	Welding Process Variables			Travel Speed (IPM)	Joint Detail (Fillet)
			AMPS/WFS*	VOLTS	Travel		
1/4"	1	.052"	265-320	31-34.5	13-16	<p>Show all dimensions, weld sizes, passes, and AWS symbols</p> <p>T1 = Varies T2 = Varies S = Weld Size</p> <p> T1 & T2 equal to or less than 3/4" for 1/4" welds.</p>	
5/16"	1	.052"	265-320	31-34.5	13-16		
3/8"	1-3	.052"	265-320	31-34.5	13-16		
7/16"	2-4	.052"	265-320	31-34.5	13-16		
1/2"	4-6	.052"	265-320	31-34.5	13-16		
5/8"	5-7	.052"	265-320	31-34.5	13-16		
3/4"	6-8	.052"	265-320	31-34.5	13-16		

* Wire feed speed may be used along with amperage (include chart)

Prepared By: James R. Connor DSB QA Manager

Project: Granite Street over Stevens Branch of the Winoski River

DSB Job: 12550-1042

Preheat and Interpass Temperature Chart		
Base Metal Thickness range	Minimum Preheat (°F)	Max Preheat & Interpass (°F)
≤ 3/4"	50°F	450°F
>3/4" to ≤ 1.5"	70°F	450°F
>1.5" to ≤ 2.5"	150°F	450°F
> 2.5"	225°F	450°F

Note: When this procedure is used for A709Gr50W materials, it shall be limited to 5/16" single pass or material be coated.