

DSBROWN Production Joint Welding Procedure Specification (D1.5-02)


Procedure No: A-(MC)GSV-01 Date Issued: 9-29-04 Revision No: 0 Rev. Date: _____

Contractor (Fabricator) D. S. Brown Company Prepared by: James R. Connor, Quality Assurance Manager

1. Non-Fracture Critical Fracture Critical WPS Expiration Date: _____
2. Qualified in accordance with: AWS D1.5-2002 (5.12.1)
 Referenced PQR No(s): PQR-(MC)GMAW-01(04)
 Referenced FWST No(s): _____
3. Material specification(s) ASTM A709 Gr. 36, 50, 50W For DOT Approval
4. Material Thickness (es) Unlimited
5. Welding process GMAW
6. Manual , machine , or semiautomatic
7. Position(s) of welding 1G, 2G
8. Filler metal specification AWS A5.18
9. Filler metal class and brand name E70C-6M Corex Metal-Core Maxim
10. Flux class & brand N/A, Type N/A
11. Shielding gas 75% Ar / 25% CO2 Flow rate 45 CFH
12. Single pass Or multiple pass
13. Single arc Or multiple arc
14. Welding Current DCEP
15. Polarity Reverse
16. Welding progression stringers
17. Root treatment Clean to bright sound metal or per AWS D1.5 (3.2.1 & 3.11)
18. Postheat treatment N/A
19. Calculated Heat Input (KJ/in) Min 30.6 KJ/in Max 51.1 KJ/in
20. Electrode extension (electrical stickout) 3/4"

V.A.O.T. RECEIVED
 NOV 1 12 2004
 APPROVED BY _____ DATE 11-30-04

Weld size (in)	Pass No(s)	Electrode Size (in)	Welding Process Variables		Travel Speed (in/min)	Tapered
			AMPS	VOLTS		
1/4"	1	.052"	265-320	31-34.5	13-16	
5/16"	1-2	.052"	265-320	31-34.5	13-16	
3/8"	1-3	.052"	265-320	31-34.5	13-16	
1/2"	3-4	.052"	265-320	31-34.5	13-16	
5/8"	4-6	.052"	265-320	31-34.5	13-16	
3/4"	5-8	.052"	265-320	31-34.5	13-16	



T1 = 1/4" min.
 T2 = Unlimited
 f = 1/8" min.
 R = 0
 alpha = 60°
 S = Groove Prep Depth

For Butt Joints see AWS 2.14

Preheat and Interpass Temperature Chart		
Base Metal Thickness range	Minimum Preheat (°F)	Max Preheat & Interpass (°F)
≤ 3/4"	50°F	450°F
>3/4" to ≤1.5"	70°F	450°F
>1.5" to ≤2.5"	150°F	450°F
>2.5"	225°F	450°F

Prepared By: James R. Connor DSB QA Manager
 Project: Granite Street over Stevens Branch of the Winooski River

DSB Job: 12550-1042

Note: When this procedure is used for A709Gr50W materials, it shall be limited to 5/16" single pass or material be coated.