



TABLE 704.02A - GRAVEL FOR SIDE DRIVE

Gravel	Percentage by Weight Testing Source from Stone	Gravel	Percentage by Weight Testing Source from Stone
No. 4	20 - 60	No. 100	22
No. 100	0 - 100	No. 200	12

The above portion of the gravel shall be uniformly graded from coarse to fine, and the maximum size of particles shall not exceed 2 1/2 times the size of the largest particles in the coarse portion.

(b) Percent of Water: The percent of water of the gravel shall be not more than 20 when tested in accordance with ASTM D 155, or more than 40 when tested in accordance with ASTM D 94.

TABLE 704.02B - GRAVEL DRIVE FOR SIDE DRIVE

Gravel	Percentage by Weight Testing Source from Stone	Gravel	Percentage by Weight Testing Source from Stone
No. 4	25 - 50	No. 100	25
No. 100	0 - 25	No. 200	15






(a) Grading: The gravel shall be uniformly graded from coarse to fine, and the maximum size of particles shall not exceed 2 1/2 times the size of the largest particles in the coarse portion.

(b) Percent of Water: The percent of water of the gravel shall be not more than 20 when tested in accordance with ASTM D 155, or more than 40 when tested in accordance with ASTM D 94.

(c) Fractured Faces: At least 20 percent, by weight, of the stone content shall have fractured faces.

Fractured faces will be determined on the vertical surface of the No. 4 stone.

NO	DATE	DESCRIPTION	PRINTS
1	10/28/19	REVISED	5 @ 1/4"
2	10/28/19	WELLMAN, ARCHITECTS	2 @ 1/4"
3	10/28/19	B. GOUGHNOUR	3 @ 1/4"



NOTE:
THIS DRAWING TO BE USED IN CONJUNCTION WITH DRAWING 1-4
REVISED 10/28/19
DATE: 10/28/19
DRAWN BY: [Signature]
APPROVED BY: [Signature]

STATE OF VERMONT
DIVISION OF STATE BUILDINGS
AGENCY OF ADMINISTRATION
MONTPELIER, VERMONT

FAIR HAVEN WELCOME CENTER
DEVELOPED SITE PLAN

NO.	DATE	REVISION	SCALE	DWG. NO.
1	10-28-19	1-40	1"=40'	1A

REVISIONS: [Blank]

DRAWING NO. 1-A

SCALE: 1"=40'

DATE: 10/28/19

DRAWN BY: [Signature]

CHECKED BY: [Signature]

PROJECT: 7504